

Your application

Your Permastore Solution

Internal Color

Ecofusion™ for

- Livestock effluent tanks
- Moist grain silos
- Light duty industrial solids

Application: pH 4 - 8

Type: 2 coat, 1 fire

Thickness: 7.1 - 11.0 MILS

Test regime: BS 7793 part 1

Isofusion® for

- Potable water
- Municipal sewage treatment
- Fire water
- Forage silos
- Bulk solids

Application: pH 3 - 9

Type: 2 coat, 1 fire

Thickness: 7.1 - 11.0 MILS

Test regime: Zero discontinuities at 9V

wet swab salt solution

Exceeds requirements of DEZ 4.12

Trifusion® for

- Industrial effluents
- Underground slurry pits
- Tank floors

Application: pH 2 - 11

Type: 3 coat, 2 fire

Thickness: 11.0 - 15.0 MILS

Test regime: Zero discontinuities at 1000V

Exceeds requirements of DEZ 4.13 and

BS 7793 part 2, 1996

Trifusion® Plus for

- More aggressive industrial applications

Application: pH 1 - 14

Type: 3 coat, 2 fire

Thickness: 13.3 - 16.5 MILS

Test regime: Zero discontinuities at 1500V

Exceeds requirements of DEZ 4.13 and

BS 7793 part 2, 1996

A detailed specification is available on request. A Zero Defects policy applies to Isofusion®, Trifusion® and Trifusion® Plus for the tests shown. All applications are subject to concentration and temperature considerations. All specifications relate to the internal surfaces only.



20 - C - 40
(RAL 5013)

20 - C - 40
(RAL 5013)

14 - C - 40
(RAL 7009)

14 - C - 40
(RAL 7009)

STANDARD EXTERNAL COLORS

A limited range of alternative external colors is available on request. All color identification numbers are the closest visual match only. All panel exteriors are Glass-Fused-to-Steel environmental specification.

12 - B - 29
(RAL 6006)
MUNSELL 2.5 GY 2/2

20 - C - 40
(RAL 5013)
MUNSELL 5PB 2/4